SUNCONTROL®

GARWARE WINDOW FILM

MECHANICAL PROPERTIES:

THICKNESS OF FILM (MIL)	08
TENSILE STRENGTH AT BREAK(MD/TD)	>2000 KG/CM
ELONGATION AT BREAK MD	>170%
PEEL STRENGTH	- ABOVE 3.25 KG/Inch
IMPACT TEST Bs6206 FOR CLASS 'A'	- PASSES

SOLAR PROPERTIES:

% VISIBLE LIGHT TRANSMITTANCE	- 91
SHADING COEFFICIENT	- 0.98
EMMISIVITY	- 0.88
U FACTOR	- 1.12
% ULTRA VIOLET REJECTION	- 99
% TOTAL SOLAR ENERGY REJECTED	- 15

Tests are representative of actual production sample & may vary from batch to batch.

Safety 8 Mil